

### Auxiliaries and equipment

#### Applications

Adhesive for eboard W / eblock W  
Adhesive for eboard 1700 / eblock 1700

#### Properties

no run-off on vertical surfaces

#### Processing data

Product		Mixture	Resin	Hardener
		ebafix grau / H 2017	ebafix grau	H 2017
Colour		grey	grey	amber
<b>Mixing ratio</b>	<b>p.b.w.</b>		100	10
Viscosity at 25 °C	mPas	pasty	pasty	440 ± 100
Density at 20 °C	g/cm <sup>3</sup>	1,65 ± 0,05	1,75 ± 0,05	1,04 ± 0,02
Pot Life	Minutes	30 - 40		
Demoulding time	Hours	16 - 24		

#### Physical data

Properties	Inspect. Requirements	Unit	Value
Flexural strength	EN ISO 178*	MPa	103 ± 10
Flexural elongation at break	EN ISO 178*	%	2,1 ± 0,,3
Flexural modulus	EN ISO 178*	MPa	7050 ± 150
Compressive strength	EN 604*	MPa	113 ± 10
Impact resistance (Charpy)	EN ISO 179*	kJ/m <sup>2</sup>	18 ± 3
Heat deflection temperature HDT	DIN EN ISO 75-1*	°C	103 ± 3
Shore hardness	DIN ISO 48-4*	Shore D	90 ± 3

\* based on

#### Sales units (packages)

ebafix grey resin, 0,375 kg tin  
H 2017 amber hardener, 0.045 kg tin

#### additional products

cleaning agent ebaclean, colourless 5 l can

### **Processing instructions**

Material- and processing temperature: between 18 - 25 °C.  
Close containers after use.

The mixing ratio of resin and hardener must be adhered to according to the specifications.

Components A and B must be mixed thoroughly.

We recommend applying the adhesive with a fine notched spatula.

Consumption: approx. 600-700 g/m<sup>2</sup>

Resin residues on stirring rods etc. can be easily cleaned with ebaclean.

### **General**

ebafix is a two-component polyurethane-based system that cures at room temperature.

To accelerate bonding, ebafix can be mixed with our repair putty according to the mixing chart.

The repair putty can also be used on its own as a fast adhesive or for repair work.

All specified characteristic values were determined after thermal conditioning at 80 °C for 8 hours.  
The pot life was determined in accordance with internal test procedures using a 200 g sample at room temperature (approx. 23 °C).  
The demolding times refer to demolding at room temperature.

### **Storing**

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Please refer to the product labels for the shelf life of the material.

### **Safety measure**

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material.

Please refer to the respective safety data sheets

### **Waste Disposal**

The cured materials can be disposed of as household or commercial waste in consultation with the respective competent authority.

Uncured products must be properly disposed of in consultation with the competent authority.

For further questions, our product safety department is at your disposal.

### **Compliance & Legal**

The information and recommendations provided are based on careful evaluation and practical experience. They reflect the state of our knowledge at the time of provision. Updates may be made without notice.

The information is intended as general guidance and does not constitute a warranty of specific characteristics or properties of the product. Due to the wide range of potential applications and processing methods, not all individual use cases can be covered. The product must be used in accordance with the applicable safety and usage instructions. No liability will be accepted for improper use or application outside the intended purpose.

Unless otherwise agreed, it is the responsibility of the user to independently assess the suitability of the product for the intended application and processing method.

The information provided does not release the user from the obligation to seek individual advice in cases of uncertainty regarding specific applications.

Statutory warranty rights remain unaffected.