

repair putty turquoise / PUR 50

Technical Datasheet



Auxiliaries and equipment

Applications

Repair putty for ebaboard 0750

Properties

no run-off on vertical surfaces

heat resistance 85 °C

Processing data

Product		Mixture	Resin	Hardener
		repair putty turquoise / PUR 50	repair putty turquoise	PUR 50
Colour		turquoise	turquoise	brown
Mixing ratio	p.b.w.		100	50
Viscosity at 25 °C	mPas	pasty	pasty	120 ± 20
Density at 20 °C	g/cm ³	1,34 ± 0,03	1,38 ± 0,03	1,23 ± 0,02
Pot Life	minutes	4 - 7		
Demoulding time	hours	2 - 4		

Physical data

Properties	Inspect. Requirements	Unit	Value
Flexural strength	DIN EN ISO 178*	MPa	72 ± 5
Flexural elongation at break	DIN EN ISO 178*	%	6,0 ± 0,5
Flexural modulus	DIN EN ISO 178*	MPa	2500 ± 300
Compressive strength	DIN EN ISO 604*	MPa	73 ± 5
Heat deflection temperature HDT	DIN EN ISO 75 B*	°C	85 ± 3
Shore hardness	DIN ISO 48-4*	Shore D	86 ± 3

* based on

Sales units (packages)

repair putty turquoise comp.A, 1 kg

PUR 50 brown comp. B 0,500 kg bottle

additional products

ebafix turquoise comp.A, 1 kg

cleaning agent ebaclean, colourless 5 l can

repair putty turquoise / PUR 50

Technical Datasheet



Processing instructions

Material- and processing temperature: between 18 - 25 °C.
Close containers after use.

The mixing ratio of resin and hardener must be adhered to according to the specifications.

Components A and B must be mixed thoroughly.

When using the repair putty for repair works, the putty can be applied with a spatula.

When using the repair putty as an adhesive, we recommend applying it with a fine notched spatula.

Consumption: approx. 600-700 g/m²

Resin residues on stirring rods, etc., can be easily cleaned with ebaclean.

General

The repair putty is a two-component polyurethane-based system that cures at room temperature.

The repair putty can be used as a fast adhesive or for repair work.

To slow down the reaction, the repair putty can be mixed with our adhesive ebafix according to the mixing chart.

All specified characteristic values were determined after thermal conditioning at 80 °C for 8 hours.

The pot life was determined in accordance with internal test procedures using a 200 g sample at room temperature (approx. 23 °C).

The demolding times refer to demolding at room temperature.

Storing

Storage at room temperature 18-25 °C.

Opened containers should be closed immediately after use and should be used up as soon as possible.

Please refer to the product labels for the shelf life of the material.

Safety measure

Please follow the precaution instructions of the Government Safety Organisation of the chemical industry when working with this material.

Please refer to the respective safety data sheets

Waste Disposal

The cured materials can be disposed of as household or commercial waste in consultation with the respective competent authority.

Uncured products must be properly disposed of in consultation with the competent authority.

For further questions, our product safety department is at your disposal.

Compliance & Legal

The information and recommendations provided are based on careful evaluation and practical experience. They reflect the state of our knowledge at the time of provision. Updates may be made without notice.

The information is intended as general guidance and does not constitute a warranty of specific characteristics or properties of the product. Due to the wide range of potential applications and processing methods, not all individual use cases can be covered.

repair putty turquoise / PUR 50

Technical Datasheet



The product must be used in accordance with the applicable safety and usage instructions. No liability will be accepted for improper use or application outside the intended purpose.

Unless otherwise agreed, it is the responsibility of the user to independently assess the suitability of the product for the intended application and processing method.

The information provided does not release the user from the obligation to seek individual advice in cases of uncertainty regarding specific applications.

Statutory warranty rights remain unaffected.