

Shore hardness GM 952

GM 952 Comp. C in % p.b.w. to Comp. A

MV 100 : 11,5

Comp. A	100 g	100 g	100 g	100 g	100 g	100 g	100 g
Comp. B	11,5 g	11,5 g	11,5 g	11,5 g	11,5 g	11,5 g	11,5 g
Comp. C weight	5 g	7,5 g	10 g	15 g	20 g	22,5 g	25 g
Comp. C in %	5	7,5	10	15	20	22,5	25
Shore A after 24 h RT	33 – 35	29 – 32	27 – 28	22 – 23	18 – 20	15 – 17	14 – 15
Shore A after 8 h/80°C	42 – 43	39 – 40	35 – 36	32 – 33	26 – 28	24 – 25	20 – 22

First mix Comp. A and Comp. C, then add Comp. B.