

Mixing ratios for adjusting pot life

Repair putty orange / ebafix orange

Repair putty orange Comp. A (amount in g)	ebafix orange Comp. A (amount in g)	PUR 50 Comp. B (amount in g)	Pot life at 20 °C (min)
100	0	50	approx. 6
80	20	50	approx. 7
60	40	50	approx. 8
50	50	50	approx. 9
40	60	50	approx. 11
30	70	50	approx. 12
20	80	50	approx. 13
10	90	50	approx. 16
0	100	50	approx. 18